

ITEMS (1) (5)			Cooling water (3)			Cooled water		Heated water (2)				Tendency if out of criteria
			Circulating system		Once flow			Low temperature		High temperature		
			Circulating water	Supply water (4)	Flowing water	Circulating water [below 20°C]	Supply water (4)	Circulating water [20°C~60°C]	Supply water (4)	Circulating water [60°C~80°C]	Supply water (4)	
ITEMS TO BE CONTROLLED	pH	at 25°C	6.5~8.2	6.0~8.0	6.8~8.0	6.8~8.0	6.8~8.0	7.0~8.0	7.0~8.0	7.0~8.0	7.0~8.0	corrosion + scale
	Electrical conductivity	[mS/m] at 25°C	below 80	below 30	below 40	below 40	below 30	below 30	below 30	below 30	below 30	corrosion + scale
		(μS/cm) At 25°C(1)	(below 800)	(below 300)	(below 400)	(below 400)	(below 300)	(below 300)	(below 300)	(below 300)	(below 300)	corrosion + scale
	Chloride ion	[mgCl ⁻ /l]	below 200	below 50	below 50	below 50	below 50	below 50	below 50	below 30	below 30	corrosion
	Sulfate ion	[mgSO ₄ ²⁻ /l]	below 200	below 50	below 50	below 50	below 50	below 50	below 50	below 30	below 30	corrosion
	M-alkalinity (pH4.8)	[mgCaCO ₃ /l]	below 100	below 50	below 50	below 50	below 50	below 50	below 50	below 50	below 50	scale
	Total hardness	[mgCaCO ₃ /l]	below 200	below 70	below 70	below 70	below 70	below 70	below 70	below 70	below 70	scale
	Calcium hardness	[mgCaCO ₃ /l]	below 150	below 50	below 50	below 50	below 50	below 50	below 50	below 50	below 50	scale
ITEMS TO BE REFERRED TO	Silica ion	[mgSiO ₂ /l]	below 50	below 30	below 30	below 30	below 30	below 30	below 30	below 30	below 30	scale
	Iron	[mgFe/l]	below 1.0	below 0.3	below 1.0	below 1.0	below 0.3	below 1.0	below 0.3	below 1.0	below 0.3	corrosion + scale
	Copper	[mgCu/l]	below 0.3	below 0.1	below 1.0	below 1.0	below 0.1	below 1.0	below 0.1	below 1.0	below 0.1	corrosion
	Sulfide ion	[mgS ²⁻ /l]	not detectable	not detectable	not detectable	not detectable	not detectable	not detectable	not detectable	not detectable	not detectable	corrosion
	Ammonium ion	[mgNH ₄ ⁺ /l]	below 1.0	below 0.1	below 1.0	below 1.0	below 0.1	below 0.3	below 0.1	below 0.1	below 0.1	corrosion
	Remaining chloride	[mgCl/l]	below 0.3	below 0.3	below 0.3	below 0.3	below 0.3	below 0.25	below 0.3	below 0.1	below 0.3	corrosion
	Free carbide	[mgCo ₂ /l]	below 4.0	below 4.0	below 4.0	below 4.0	below 4.0	below 0.4	below 4.0	below 0.4	below 4.0	corrosion
	Stability index		6.0~7.0	---	---	---	---	---	---	---	---	corrosion + scale

NOTES

- Names, definitions and units are according to JIS K 0101. Units and figures between brackets are old units published as reference only.
- In case of using heated water (more than 40°C), corrosion is generally noticeable.
Especially when the iron material is in direct contact with water without any protection shields, it is desirable to give the valid measures for corrosion. e.g. chemical measure,...
- In the cooling water using hermetic cooling tower, closed circuit water is according to heated water standard, and scattered water is according to cooling water standard.
- Supply water is considered drink water, industrial water and ground water except for genuine water, neutral water and soft water.
- The above mentioned items are representable items in corrosion and scale cases.